



www.parchem.com

GET A QUICK QUOTE

## Typical Product Specifications & Properties

# Aluminum Hydroxide - ALUGEL A215

CAS Number: : 21645-51-2

| Specifications               | Limits   |
|------------------------------|--|
| Density                      | 2.42   |
| Na                           | 0.5% Max.  |
| As                           | 5ppm max.  |
| Heavy Metals                 | 50 ppm max.  |
| Ph - stat test               | min. 40 ml/ 130 ml/ 270 ml 0.1 n HCl                                   |
| pH                           | 10 Max.  |
| Cl                           | 0.85% Max.   |
| Tests ACC. Ph. EuR. II BP 88 | min. pH 1.8/2.3/3.0 max. 40/ max. 35 ml                                |
| Assay                        | 50-57.5% Al <sub>2</sub> O <sub>3</sub> min. 76.5% Al(OH) <sub>3</sub> |
| Bulk density, loose          | 0.2 - 0.3 g/ml   |
| SO <sub>4</sub>              | 0.6% Max.  |
| Loss on Drying (105°C/ 2h)   | Approx. 13%  |



GET A QUICK QUOTE

415 Huguenot Street, New Rochelle, New York 10801



www.parchem.com



**parchem**  
fine & specialty chemicals

GIVE US A CALL  
800-282-3982  
914-654-6800

GET A QUICK QUOTE

| Specifications                  | Limits                   |
|---------------------------------|--------------------------|
| Rosett - Rice titration         | Min. 30 minutes          |
| Bulk Density, tapped            | 0.3 - 0.4 g/ml           |
| Acid Neutralizing Capacity, USP | 25 meq/g Min.            |
| Melting Point                   | loses water 300 c        |
| Insolubility                    | in water, alcohol        |
| Odor                            | odorless                 |
| Refractive Index                | 1.57                     |
| Molecular weight                | 78.01                    |
| Solubility                      | min. acids, caustic soda |



GET A QUICK QUOTE

415 Huguenot Street, New Rochelle, New York 10801

Disclaimer: this is a web generated product specification and property document. All information on this document is subject to reconfirmation at time of quote and order.